

<b>1</b>	<b>DESCRIPTION</b>
----------	--------------------

Decoflex is a jointed sheet of veneer pressed onto a paper fleece. This way we become a flexible sheet of real wood veneer, which is easy to handle and less sensitive to damage than an ordinary spliced sheet. Decoflex is ideal for decorating curved surfaces. Decoflex can be glued onto any kind of wooden substrate and is therefore very suitable to manufacture doors or other furniture components. It is not recommended to glue Decoflex on solid wood. Decoflex is always pre-sanded with a 150 grain but the surface has not yet been treated and must still be protected by the processor (oil or varnish). Ease of use is undoubtedly the biggest asset of this product.

**Backing:** Paper base layer in a shade in line with the selected wood type.

**Thickness:** backing: 0,1 mm; veneer: 0,6 mm<sup>(1)</sup>

**Splicing method:** bookmatch or mixmatch, other techniques upon request

**Finishing:** pre-sanded grain 150

**Applications:** This product is ideal for laminating the most common wooden substrates. Decoflex is extremely bendable and can therefore be used to decorate large arches. Postforming is not possible.

**Sizes:** regular size = 2500x1240x0,6mm or 3050x1240x0,6mm  
Tolerance on dimensions: ± 20mm; Tolerance on flatness: 60mm/m

**Possible additional surface treatments by the manufacturer:** upon request Decoflex can be treated with a soft brushing “B1” or rough cut look “S1”. Please note that special prices and minimum order quantities apply. Ask your contact person at Decospan for more information. Pre-staining and/or lacquering is not possible on Decoflex.

**Storage:**

It is advisable to keep Decoflex in a dry place with a constant temperature of at least 18°C and maintain a constant relative humidity between 50% and 60%. The products should be acclimatized for 7 days before processing. We recommend to store Decoflex horizontally, face-to-face. Avoid direct contact with the floor. The top layer of Decoflex is real wood veneer, which is likely to discolour over time. Therefore, always store Decoflex in a dark place or cover the sheets so that they are not exposed to light. Decoflex is delivered in a cardboard package (parcel service). We recommend that you remove the sheets as quickly as possible from this package and store them flat as described previously. Thus, problems with the processing are avoided. Be aware of the sharp edges when manipulating Decoflex and always carry the sheets with 2 people.

---

<sup>1</sup> Keep in mind that this is the thickness of the veneer before we process it. The final thickness may vary.

	Decoflex	25/11/2019	
	Technical Info	Version: 1.0	Page: 1

## Application:

Always apply Decoflex on both sides of the core you wish to ennoble to ensure a good stability. It is possible to use another type of backing that matches the characteristics of Decoflex. Whenever chosen, any responsibility of the manufacturer expires. Under all circumstances, it is recommended to test the adhesion and stability before proceeding to full production.

Decoflex, glue, substrates and finishing products should be stored in the same area or at least at the same temperature and humidity for at least 48 hours. The recommended temperature is at least 18°C and the relative humidity is between 50% and 60%. If these parameters are not respected, this can lead to ridges between the Decoflex and the substrate.

Decoflex can be manually glued with contact glue or in a press (hot, max 70°C, and cold). Always pay carefully attention to the instructions of the glue manufacturer. When using a spray-gun it is recommended to spray several thin layers instead of 1 thick layer onto both the Decoflex and the substrate, with the necessary waiting time between the different layers. If the gluing is done by a press, then it is recommended to use a PVCA-glue or a UF-glue.

Before applying the glue, ensure that all surfaces are free of grease, dust and other dirt. The surface can be cleaned efficiently by denaturized ethyl alcohol. For contact glue it is important that the glue is applied on both surfaces. If using a glue spatula, apply the glue on one surface at right angles to the other.

Start to press from the middle of the board (never begin from the sides). Once the two surfaces are making contact they can be properly pressed by using a roller with two grips. Use body weight for maximum pressure. Never use a hammer and block or rollers with only one grip!

**Finishing:** Decoflex can be finished like any other wood veneered board. It is preferable to leave 4 or 5 days between gluing and finishing Decoflex to be sure that all the solvents from the glue have disappeared. Make sure the surface is clean and polished with the correct abrasive technique. Always follow the instructions of the supplier of stain/lacquer/oil.

## 2 TECHNICAL DATA MANUFACTURER

Thickness of the top layer	EN 14354	0,6 mm
Deviation of thickness	EN 14354	≤ 0,3 mm
Deviation of squareness	EN 324-2	± 5 mm/m
Tolerance on flatness	-	60 mm/m
Tolerance on dimensions	-	± 20 mm
Cup in width direction	EN 14354	5 %
Flatness deviation	EN 14354	5 %
Veneer gluing adhesion	EN 204/205	≥ 1 N/mm <sup>2</sup>
Density	EN 323/EN672	1300 kg/m <sup>3</sup>
Moisture content	EN 322	5 % - 9 %

	Decoflex	25/11/2019	
	Technical Info	Version: 1.0	Page: 2

<b>3</b>	<b>OTHER DOCUMENTS</b>
----------	------------------------

- Pure Wood Charter
- FSC® Certificate
- PEFC Certificate

<b>4</b>	<b>CONTACT DETAILS</b>
----------	------------------------

In case of clarity or additional questions, please contact Decospan NV.

**Decospan NV**

Industriezone Grensland

Lageweg 33

8930 Menen – Belgium

T: +32 56 52 88 00

E-mail: [info@decospa.com](mailto:info@decospa.com)

The information is obtained with utmost care and the results are compiled by reliable sources. The herein contained information and data are considered to be accurate and correct, with reservation of misprints, norm errors or other mistakes. Decospan makes no warranty of any kind, expressed or implied, concerning the accuracy or completeness of the information. Decospan will not be liable for claims relating to any party's use of or reliance on information and data contained herein, regardless of whether it is claimed that the info is inaccurate, incomplete or otherwise misleading. It is offered for your consideration, investigation and verification. Due to possible technical changes it is the user's responsibility to obtain the most up to date information.

	Decoflex	25/11/2019	
	Technical Info	Version: 1.0	Page: 3